

Giant magneto-electrocatalytic effect in Ni-based electrodes

F. Longo^{1,2}, M. Suloska^{1,2}, Z. Novotny^{3,4}, P. J. Lloreda-Jurado⁵, J. Gil-Rostra⁵,
A. R. González-Elípe⁶, F. Yubero⁶, A. Borgschulte^{1,2}

¹Laboratory for Advanced Analytical Technologies, Empa, Dübendorf, Switzerland

²Department of Chemistry, University of Zurich, Zürich, Switzerland

³Swiss Light Source, Paul Scherrer Institut, Villigen-PSI, Switzerland

⁴Laboratory for Joining Technologies and Corrosion, Empa, Dübendorf, Switzerland

⁵Nanotechnology on Surfaces Group, Instituto de Ciencia de Materiales de Sevilla (ICMS-US-CSIC),
Seville, Spain

⁶Nanotechnology on Surfaces and Plasma, Institute of Materials Science of Seville (CSIC-US), Seville,
Spain

filippo.longo@empa.ch

Alkaline water electrolysis represents one of the simplest methods employed for renewable hydrogen production [1]. In contrast to acidic electrolyzers (e.g., PEM), alkaline electrolyzers reach high conversion efficiency with low-cost abundant transition metals such as Ni-Fe alloys [2]. In addition to its intrinsically high electrolytic activity for oxygen evolution reaction (OER), we show that the activity can be enhanced by more than 20% simply applying a magnetic field (Fig. 1). The understanding of the phenomenon is complex as the surface of these catalysts is subject to a dynamic equilibrium, and the presence of specific phases depends on the presently applied conditions including the magnetic field as well as on the history of the sample. Using APXPS [3] and a combination of soft- and hard x-ray photoelectron spectroscopy with electrochemical impedance spectroscopy we find that the high intrinsic electronic conductivity comes together with an increasing water intercalation into the oxyhydroxide, which is experimental evidence for a water mediated OH⁻ diffusion mechanism. Our hypothesis is that this pore structure is affected by the presence of a magnetic field to minimize the local stray field. The (re-)orientation requires restructuring of the surface explaining the time dependence of the effect.




Fig. 1. OER enhancement of NiFe under applied magnetic field.

[1] D. M. F. Santos and C. A. C. Sequeira, *Quim. Nova*, **36**, 1176 (2013).

[2] L. Trotochaud, S. L., et al., *Journal of the American Chemical Society*, **136**, 6744 (2014).

[3] Z. Novotny, et al., *Rev. Sci. Instrum.*, **91**, 023103 (2020).