## Ab-initio investigations of the order of K<sup>+</sup> ions on cleaved muscovite mica

Andrea Conti<sup>1</sup>, Giada Franceschi<sup>1</sup>, Michael Schmid<sup>1</sup>, Ulrike Diebold<sup>1</sup>, Florian Mittendorfer<sup>1</sup>

<sup>1</sup> Institute of Applied Physics, Technical University of Vienna (Austria)

conti@iap.tuwien.ac.at

Model systems based on single crystals can help to provide a better understanding of the chemistry and the catalytic activity of a given oxide surface. Muscovite mica is an interesting material due to its widespread presence in natural environments and its potential use in various technological applications, such as new-generation electronics based on 2D materials, thermal and electrical insulation, and thin-film growth.

In this work, we present DFT calculations on the surface of muscovite mica, a common phyllosilicate whose structure consists of alternating layers of aluminosilicates and  $K^+$  ions. This material easily splits into thin K-terminated sheets, yet the atomistic order of the surface  $K^+$  ions has been, until recently, unknown [1].

Ab-initio calculations using the "Vienna Ab-initio Simulation Package" (VASP) and the metaGGA ( $r^2$ SCAN) exchange-correlation functional indicate a close correlation between the distribution of the surface K<sup>+</sup> ions and the arrangement of the subsurface Al<sup>3+</sup> ions: the K<sup>+</sup> ions preferentially occupy the Al-rich rings. Moreover, the calculated diffusion barriers (between 0.7 and 1 eV) suggest that the K<sup>+</sup> ions are mobile enough at room temperature to occupy the energetically most favorable sites. AFM simulations using the Probe Particle Model [2] are in good agreement with the experimental images.




Fig. 1. Constant-height, non-contact AFM image of UHV-cleaved muscovite mica.

- [1] G. Franceschi, P. Kocán, A. Conti, S. Brandstetter, J. Balajka, I. Sokolović, M. Valtiner, F. Mittendorfer, M. Schmid, M. Setvín, U. Diebold, Nature Communications **14**, 208 (2023)
- [2] P. Hapala, G. Kichin, C. Wagner, F. S. Tautz, R. Temirov, P. Jelínek, Physical Review B 90, 085421 (2014)